

# 100% SELF CURING READY MIX PLASTER



SAVE 7-10 DAYS OF CURING



SAVE ON SUPERVISORY COSTS





BETTER CRACK RESISTANCE



LOWER LABOUR COSTS





Ramco SELF CURING PLASTER is a premixed ready made render for manual application. It is manufactured specially using high quality raw materials along with hydrophilic substance which ensures the curing chemically and delivers good adhesion properties and sag resistance. The product has been engineered to retain only that much amount of water in the mortar required for the Hydration of cement in the mortar mix.



#### MIXING

Ramco SELF CURING PLASTER - Self Curing contains all ingredients in dry form, only water needs to be added. Mix 7 liters of clean water with dry mortar until a homogeneous smooth mass is reached. If necessary add more water to get the plastic-like consistency. Do not mix longer than 5 minutes. Do not use old and hardened mortar.

# **SURFACE PREPARATION**

The wall should be dry and clean. In hot weather conditions wet the wall before application. Avoid exposure to direct sun and strong wind. If possible start application in shade.

## **APPLICATION**

For flat concrete surface use a primer such as cement slurry or a construction adhesive to improve the bonding strength. Application up to 20 mm can be made in one step without sagging. If you have different types of substrates (like brick / concrete or brick / polystyrene sheet) use fiber mesh or metal net for the joint area to avoid cracks. Before the final coat is applied RAMCO SELF CURING PLASTER needs to be hardened (minimum of 7 days depending on thickness

and weather conditions). This product can be used for all internal and external wall applications. Do not apply below 5°C. Minimal thickness: 12 mm Maximal thickness in one layer: 20 mm

# CONSUMPTION

Water: 6-7 litres per 40 kg bag. Coverage area (1 bag of 40 kg): => 1.65 to 1.85 s-m / 18 – 20 sft @ 12 mm thickness under ideal conditions.

## **APPLICATIONS**

Suitable on all mineral substrates such as bricks, concrete bricks, concrete blocks, AAC, etc.





#### Manufactured & Packed by:

# THE RAMCO CEMENTS LIMITED

F-14, Sipcot Industrial Park, Pondur, 'A' Village,

Sriperumbudur - 602106.

Customer Care No.: +91 - 44 - 2847 8666 E-mail: nraghu@ramcocements.co.in

#### **Marketing Office:**

3rd Floor, Sycon Polaris, 1/58, 8th Main, R M V Extension, Sadashivanagar, Bengaluru - 560 080.

#### Contact:

Chennai: 044 - 2811 2744, 94450 09482 / 3 / 4 / 97

Madurai: 0452 - 2342167, 94450 08190

Coimbatore: 0422 - 2552031, 94443 86493, 94450 09498 Bengaluru: 080 - 4075 0000 / 04 / 05, 99000 16104/5/6/16

Kochi: 0484 - 2374783, 94460 02239 / 6299, 94465 77702

Hyderabad: 040 - 2311 9271 / 72, 98499 12306